

Coronado Stone is manufactured to meet or exceed specifications for all major code approvals. Independent testing confirms compliance with ICC-ES AC51 for Precast Stone Veneer. Always check your local building codes before installing stone.

## MATERIALS:

- |             |                  |
|-------------|------------------|
| - Cement    | ASTM C150        |
| - Sand      | ASTM C144 or C33 |
| - Aggregate | ASTM C33 or C330 |

## TESTING:

- |                        |  |
|------------------------|--|
| - Shear Bond Test      | Tested in accordance with ASTM C482<br>Greater than 50 psi   |
| - Water Absorption     | Tested in accordance with section 3.1.4 & 4.6<br>of ICC-ES AC51  |
| - Freeze / Thaw        | Tested in accordance with ASTM C67<br>Less than 3% mass loss   |
| - Unit Weight          | Shipping weight is less than 15 lbs. per sq. ft.<br>Density is determined in accordance with ASTM C567 |
| - Compressive Strength | Tested in accordance with ASTM C39<br>Greater than 1800 psi  |
| - Tensile Strength     | Tested in accordance with ASTM C190  |
| - Flexural Strength    | Tested in accordance with ASTM C348  |
| - Thermal Resistance   | Tested in accordance with ASTM 177-71  |

